. (19) World Intellectual Property Organization International Bureau





(43) International Publication Date 18 December 2003 (18.12.2003)

PCT

(10) International Publication Number WO 03/104313 A1

(51) International Patent Classification⁷: A61L 27/56

C08J 9/28,

(21) International Application Number: PCT/SE03/00836

(22) International Filing Date: 23 May 2003 (23.05.2003)

(25) Filing Language:

Swedish

(26) Publication Language:

English

(30) Priority Data: 0201779-6 60/389,937

11 June 2002 (11.06.2002) SE 20 June 2002 (20.06.2002) US

(71) Applicant (for all designated States except US): TERMI-NUS BIOTECH AB [SE/SE]; Norra Storgatan 60, S-267 35 Bjuv (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): NILSSON, Kjell [SE/SE]; Norra Storgatan 60, S-267 35 Bjuv (SE).

(74) Agent: AWAPATENT AB; Box 5117, S-200 71 Mälmo (SE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POROUS GELATIN MATERIAL, GELATIN STRUCTURES, METHODS FOR PREPARATION OF THE SAME AND USES THEREOF

(57) Abstract: The present invention relates to a porous gelatin material in the form of spherical particles with a continuous pore structure and cast, three-dimensional, porous gelatin structures. The invention also comprises methods for preparation of said porous gelatin materials and structures. The method for preparing the porous gelatin material in the form of spheres with a continuous pore structure comprises the steps of preparing a homogenous water-based gelatin solution, adding an emulsifier with an HLD value >9, adding a first composition comprising an organic solvent and an emulsifier with an HLB value >9, adding a second composition comprising an organic solvent and an emulsifier with an HLB value <8 and allowing the gelatin material to solidify. Uses of the materials according to the invention are also included.